

Ph: +61 2 9609 5090 E: sales@gantiel.com 4 Davis Road, Wetherill Park, NSW 2164 P.O.Box 586 Baulkham Hills NSW 1755

ABN: 87 108 071 512

Gantiel Vensott Engineering Plastic Solutions

Product Information

Trade name:	Venlon 6EB
Designation:	Polyamide 6 Extruded
Type of polymer:	Thermoplastic
Food compliance BfR	Yes
Food compliance FDA:	Yes
Colour:	Black

Product Description

Venlon 6EB is a general-purpose grade plastic that offers an excellent blend of mechanical and impact strength, vibration damping, wear and creep resistance. Complimenting these properties are good electrical insulation and favorable chemical resistance. Widely used for washers and gasket applications. Venlon 6EB is applicable within a temperature range of -40 to +160 °C.

Properties

Density:	1.14	g/cm³	ISO 1183
Tensile modulus of elasticity:	3,250	MPa	ISO 527-2
Specific surface resistance:	10 ¹³	Ohm	IEC 60093
Temperature for usage in air:	160	°C	
(max. short term)			

Applications

- Support and guide wheels
- Sleeves for wheels and rollers
- Insulators
- Flanges
- Feed Screws/Scrolls

- Conveyor rollers
- Cams
- Sealing rings
- Impact Rollers

Key Features and Benefits

- High mechanical strength
- Tough and impact resistant
- Good resilience
- Good chemical resistance

- Good fatigue resistance
- Good wear resistance
- Can be bonded







Delivery Program	
Rods - Outside diameter	6mm/8mm/10mm/12mm/16mm/20mm
Rods – Length	3000mm
Sheets – Thickness	1mm/1.5mm/2mm/3mm/5mm/6mm
Sheets – Size	2000mm x 1000mm
Tube – OD and ID	7.82mm OD x 6.15mm ID
	12.7mm OD x 9.53mm ID
	15.88mm OD x 12.7mm ID
Tube – Length	1500mm
Tolerance on length:	0% to +3%
Tolerance on width:	+1% to +4%

All information supplied by or on behalf of Gantiel Vensott Pty. Ltd. In relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Gantiel Vensott Pty. Ltd. assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Gantiel Vensott Pty. Ltd. For any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.