

# Venslide MD FG (Pastel Blue)

## Technical Data Sheet



**Gantiel Vensott**  
**Engineering Plastic Solutions**

Ph: +61 2 9609 5090 E: sales@gantiel.com  
4 Davis Road, Wetherill Park, NSW 2164  
P.O.Box 586 Baulkham Hills NSW 1755  
ABN: 87 108 071 512

### **Product Description**

Indispensable in the food sector. Venslide MD FG combines the properties of a high-quality plastic with the detectability that is required in the food sector. Plastic particles of plant components can be found and removed by all commonly available metal detectors. This means that using Venslide MD FG can enable increased food safety.

### **Applications**

- Machined Parts
- Medical Industry
- Scrapers
- Food Industry
- Wear Strips
- Wear Resistant Bearings
- Profiles and Segments
- Chain Guides

### **Key Features and Benefits**

- Metal-Detectable
- Very Good Slide Properties
- Heat Stabilized
- Excellent Shock and Impact Resistance
- Good Anti-Adhesion Properties

All information supplied by or on behalf of Gantiel Vensott Pty. Ltd. in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Gantiel Vensott Pty. Ltd. assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Gantiel Vensott Pty. Ltd. For any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.

Revision May 2020

# Venslide MD FG (Pastel Blue)

## Technical Data Sheet

### Technical Properties

	Value	Unit	DIN	ISO/EC
Molecular Weight	9x10 <sup>6</sup>	g/mol		
Code	1.1			15527:2013
Density	~1.14	Kg/dm <sup>3</sup>	53479	1183
Water Absorption – saturation at 23°C	<0,01	%	53715	

### Mechanical Properties

	Value	Unit	DIN	ISO/EC
Yield/Break stress	~20	MPa	53455	527
Breaking elongation	>200	%	53455	527
Zug-E-Modul	>600	MPa	53457	
Notch impact Strength – Charpy	≥100	kJ/m <sup>2</sup>	53453	179
Shore hardness D	62-64	°	868	7619-1
Ball hardness	>35	N/mm <sup>2</sup>	53456	2039
Sand Slurry Test	100	%		15527
Coefficient of sliding friction Steel (0.25m/s, 0.25N/mm <sup>2</sup> )	~0.2			
Coefficient of sliding friction POM (0.25m/s, 0.25N/mm <sup>2</sup> )				

### Electric Properties

	Value	Unit		Verification
Electrical strength	≤45	KV/mm	53481	60243
Specific constant resistance	>10 <sup>12</sup>	Ω x cm	53482	60093
Surface resistance	>10 <sup>12</sup>	Ω	53482	60093

### Thermal Properties

	Value	Unit	DIN	ISO/EC
Melting point	130-135	°C		3146 method C
Heat conductivity 23°C	0.4	W (K x m)	52612	
Linear thermal coefficient of expansion α (average value between 23 and 60 °C)	20x10 <sup>-5</sup>	m/(K x m)	53752	11359-2
Upper service Temperature in air short term	120	°C		
Upper service Temperature in air constant (5000h)	100	°C	53446	
Lower service Temperature	-200	°C		
Burning behavior per UL94 – sample thickness 3/6mm	HB			

### Physiological properties

	Value	Unit	DIN	ISO/EC
Approved for use in food industry (FDA)	Yes			
Approved for use in food industry (EU)	No			

The values shown in the table, enable to compare materials faster. These values are short-term values, which can be influenced by processing, environmental as well as application conditions. Therefore, these values do not represent assured properties. It is due to the customer's responsibility whether the chosen material is suitable for its specific application.